

ASTM Property

starex®	Grade	SF-401 H
	Resin Type	EPS

Typical Application : Small size package, I.C.F

Item	Measuring Method	Unit	Value
Bead Analysis			
Beads Size	JIS Z8801	mm	0.50 ~ 0.72
Ps	Polymer	%	93 ~ 94
Blowing Agent	Pentane	%	6 ~ 7
Specific Gravity		-	1.03 ~ 1.05
Best Density Range		kg/m ³	18 ~ 25
Pre-Expansion			
Expandability	Expansion for 5min CHEIL METHOD	Times	75
Blocking(Max.)		%	2
Molding Property			
Compressive Strength(Min.)	KS M 3808	N/cm ²	12 (@ 20kg/m ³)
Flexural Breaking	KS M 3808	N	35 (@ 20kg/m ³)
Fusion(Min.)	CHEIL METHOD	%	60
Thermal			
Thermal Conductivity	KS L9016	W/m.k	0.038 (@ 20kg/m ³)
Flammability			
Flammability	UL 94	-	HF-1
Flammability	KS M ISO 9772	sec / mm	5 / 44

1. The value above is the representative value of the NP standard and may have deviation. It can only be used for selecting materials.
2. The value above shall not be regarded as a material specification and cannot be used for molding designs.

Information inserted in this document such as data, statements, representative values, etc. are provided solely for customer convenience. It does not expressly or impliedly guarantee anything regarding the safety or practicability of the (1)materials, (2)products, and/or (3)design that utilizes recommendations or proposals of LOTTE Advanced Materials. Furthermore, nothing in the contents of this document shall have any legal binding effect, and especially, the representative value is simply for reference and is not a minimum value that has legal bining effect. Whether materials and/or products of LOTTE Advanced Materials and/or a design that uses or utilizes LOTTE Advanced Materials' recommendations or proposals are compatible with individusl uses shall be determined solely by each user and such user shall be solely responsible for any results, including but not limited to, any and all loss and damages incurred due to such uses. Users must implement and verify all testing and analyses for proving the safety and compatibility of final products that have been created or altered by using LOTTE Advanced Materials' materials or products. The data and values inserted and/or contained in this document may be changed due to quality improvement of the product without any prior notification.

※ The last update date : 5/13/2016